


Ferroelectrics. Disordered Ferroelectrics - Relaxors.



Outline

- **Ferroelctricity**
 - **Main properties**
 - **History. Discovery. Materials**
 - **Relaxors**
 - **Applications**

Ferroelectricity. Definition.


- **Ferroelectric Materials.** A ferroelectric material is a material that exhibits, over some range of temperature, a spontaneous electric polarization that can be reversed or reoriented by application of an electric field.

**An American National Standard
IEEE Standard Definitions of
Primary Ferroelectric Terms**


Ferroelectricity: Two classes of ferroelectrics

Order-Disorder



Displacement type






disorder




order




Ferroelectricity: Polarization reversible. (P-E hysteresis)



Ferroelectricity: Domains




Multi domain state



180° domain pattern


Y Lu et al. Science 1997;276:2004-2006




90° domains

Courtesy of Igor Lukyanchuk
<http://www.lukyanc.net/stories/nano-worldofdomains>



Ferroelectricity: Domains





Courtesy of Benjamin Vega-Westhoff and Scott Scharfenberg, P403, Fall2009




Courtesy of Allison Pohl, P403, Fall2009




Crystal from Forschungsinstitut für mineralische und metallische Werkstoffe -Edelsteine/Edelmetalle



Ferroelectricity: Landau-Ginzburg phenomenological theory



Vitaly Ginzburg
1916-2009



Lev Landau
1908-1968

Free energy

Order parameter (polarization)

$$F_P = \frac{1}{2}aP^2 + \frac{1}{4}bP^4 + \frac{1}{6}cP^6 + \dots - EP$$

the equilibrium solution $\frac{\partial F}{\partial P} = 0$

Electric field

Ignoring higher terms we can get the linear solution:

$$\frac{\partial F}{\partial P} = aP - E = 0 \qquad \chi = \frac{\partial P}{\partial E} = \frac{1}{a}$$


Assuming linear dependence of **a** on temperature we will have:

$$\alpha = \frac{1}{C}(T - T_c) \text{ and finally we will have Curie-Weiss law}$$


$$\chi = \frac{C}{(T - T_c)}$$

Ferroelectricity: Landau-Ginzburg phenomenological theory

In case of b>) ($C > 0$ also) We will have the solution for second order phase transition with two equilibrium points $-p_0$ and p_0 . Both these states are equivalent




Ferroelectricity: Landau-Ginzburg phenomenological theory



Including EP term can illustrate the P-E hysteretic behavior


$$F_P = \frac{1}{2}aP^2 + \frac{1}{4}bP^4 + \frac{1}{6}cP^6 + \dots - EP$$



Ferroelectricity: Susceptibility

$$\vec{P} = \epsilon_0 \chi \vec{E} \quad \vec{D} = \epsilon_0 \vec{E} + \vec{P} = \epsilon_0 \vec{E} + \epsilon_0 \chi \vec{E} = \epsilon_0 (1 + \chi) \vec{E} = \epsilon_0 \epsilon \vec{E}$$

For ferroelectrics $\epsilon \gg 1$ and $\epsilon \approx \chi$



Curie-Weiss law:

$$\epsilon = \frac{C}{(T - T_{CW})} + \epsilon_{00}$$

Ferroelectricity: Discovery

Rochelle Salt $\text{KNaC}_4\text{H}_4\text{O}_6 \cdot 4\text{H}_2\text{O}$




Elie Seignette

Potassium sodium tartrate discovered (in about 1675) by an apothecary, **Pierre Seignette**

Rochelle Salt originates from French city of La Rochelle where it was produced by **Pierre Seignette** another name of this material is Seignette salt




Rochelle Salt was used in medicine and food industry




Ferroelectricity: Discovery


Rochelle Salt $\text{KNaC}_4\text{H}_4\text{O}_6 \cdot 4\text{H}_2\text{O}$



Paul-Jacques Curie
1856 – 1941



Pierre Curie
1859-1906



Brothers Curie discovered and investigated the piezoelectric effect in several materials including Rochelle salt

Ferroelectricity: Discovery





Fig3. Piezoelectric response as a function of temperature [2]




Fig.1. The first published hysteresis loop [1]




Joseph Valasek (1897-1993)
University of Minnesota

1. J. Valasek, Phys. Rev. 17, 475 (1921)
2. J. Valasek, Phys. Rev. 19, 478 (1922)

Rochelle Salt $\text{KNaC}_4\text{H}_4\text{O}_6 \cdot 4\text{H}_2\text{O}$

Ferroelectricity. Terminology.



ferrum (Lat) gave the name of the broad class of magnetic materials – *ferromagnetics*

Fe has no relation to the phenomenon of *ferroelectricity* but because of a lot of common features of *ferroelectric* phase transition to *ferromagnetic* the “new” class of dielectrics was named as *ferroelectrics*.

There is another name for this class of materials - Seignette-electrics named after the alternative name of the Rochelle salt

Ferroelectrics, 1987, Vol. 71, pp. 15–16
Photocopying permitted by license only

© 1987 Gordon and Breach Science Publishers S.A.
Printed in the United States of America

A NEW SEIGNETTE-ELECTRIC SUBSTANCE

Translated from *Naturwiss.* **23** 737 (1935) by G. Busch

G. BUSCH and P. SCHERRER

Physikalisches Institut der Technischen Hochschule, Zürich,

(Received August 26, 1935)

Materials. KDP

KDP (KH_2PO_4) - potassium dihydrophosphate

1935

G. Busch and P. Scherrer, Naturwiss. **23**, 737 (1935). Eine neue *Seignetteelektrische* Substanz.



Georg Busch
1908-2000



Paul Scherrer
1890-1969




Fig. 1. Temperaturverlauf der Dielektrizitätskonstanten ϵ_{33} an KH_2PO_4 .



DIE NATURWISSENSCHAFTEN

23. Jahrgang

25. Oktober 1935


Heft 43

Eine neue seignette-elektrische Substanz.



Materials. KDP

KDP (KH_2PO_4) - potassium dihydrophosphate

$T_c \sim 123\text{K}$



KDP project (2): Graph6



Courtesy of Tim S. Thorp, Zhangji Zhao, Physics 403, Spring 2013

Courtesy of Alison Pohl, Physics 403, Spring 2009

Materials. Barium Titanate.

1943 – material with high (>1200) value of the dielectric constant (Wainer, Solomon (USA); Wul, Goldman (USSR))

1945 – discovered the ferroelectric properties of BaTiO_3 A. von Hippel (USA); Wul, Goldman (USSR))





FIG. 6. Dielectric constant and loss of barium titanate ceramic.







FIG. 15. Confirmation of Curie-Weiss laws in $(\text{Ba-Sr})\text{TiO}_3$ (400 kc).

$T_c \sim 400\text{K}$







Arthur R. von Hippel
1898-2003



A. Von Hippel, Rev. Mod. Phys. 22,221, 1950

Materials. Barium Titanate.



Walter J. Merz, Phys. Rev. 76, 1221, 1949

Materials. BaTiO₃. Domains.







FIG. 4. Surface of an a -domain crystal showing 90° walls and antiparallel domains.



Physics 403 Lab, August 2011

John A. Hooton, Walter J. Merz, Phys. Rev. 98, 409,1955


Materials. BaTiO₃. P-E hysteresis.



Courtesy of Liu M. & Lopez P,
Physics 403, Spring 2013

Ferroelectricity: Typical ferroelectric materials

		$T_c(K)$	$P_s (\mu C/cm^2)$
KDP type	KH_2PO_4	123	4.75
	KD_2PO_4	213	4.83
	RbH_2PO_4	147	5.6
Perovskites	$BaTiO_3$	408	26
	$KNbO_3$	708	30
	$PbTiO_3$	765	>50
	$LiTiO_3$	938	50
	$LiNbO_3$	1480	71



Number of publications concerning ferroelectricity. From Jan Fousek "Joseph Valasek and the Discovery of Ferroelectricity"

New Perovskite Materials - Relaxors

B-site complex	Lead magnesium niobate (PMN)	$\text{PbMg}_{1/3}\text{Nb}_{2/3}\text{O}_3$
	Lead scandium tantalate (PST)	$\text{PbSc}_{1/2}\text{Ta}_{1/2}\text{O}_3$
	Lead zinc niobate (PZN)	$\text{PbZn}_{1/2}\text{Nb}_{1/2}\text{O}_3$
	Lead indium niobate (PIN)	$\text{PbIn}_{1/2}\text{Nb}_{1/2}\text{O}_3$
A-site complex	Lead lanthanum titanate (PLT)	$\text{Pb}_{1-x}\text{La}_x\text{TiO}_3$
Both sites complex	Lead lanthanum zirconate titanate (PLZT)	$\text{Pb}_{1-x}\text{La}_x\text{Zr}_y\text{Ti}_{1-y}\text{O}_3$
	Potassium lead zinc niobate	$\text{K}_{1/3}\text{Pb}_{2/3}\text{Zn}_{2/9}\text{Nb}_{7/9}\text{O}_3$



L. Eric Cross¹



Smolenskii G.A.²
1910 - 1986




1. Pennsylvania State University, USA
2. A.F. Ioffe Institute, USSR



typical complex oxides with perovskite structure

Perovskite Structure




Perovskite is a mineral CaTiO_3 . The mineral was discovered in the Ural Mountains of Russia by Gustav Rose in 1839 and is named after Russian mineralogist Lev Perovski.



Gustav Rose
1798-1873




Lev Perovski
1792-1856



typical complex oxides with
perovskite structure

Relaxors


Regular ferroelectric BaTiO_3



$T > T_c$ (cubic)



Relaxor - PMN $\text{Pb}(\text{Mg}_{1/3}\text{Nb}_{2/3})\text{O}_3$




(cubic)



Relaxors


Regular ferroelectric BaTiO_3



$T < T_c$ (tetragonal)




Relaxor - PMN $\text{Pb}(\text{Mg}_{1/3}\text{Nb}_{2/3})\text{O}_3$



(cubic)



Relaxor. PMN dielectric susceptibility





ϵ'_{\max} and T_{\max} depend on the measuring frequency

ϵ' does not follow Curie-Weiss law


Temperature dependencies of ϵ' measured in a broad frequency range: 3mHz -1MHz

PMN. Vogel – Fulcher dependence





$$f_{\max} = f_0 \exp \left[\frac{-E_0}{T - T_{VF}} \right]$$

PMN. Frequency Dispersion.



PMN. Frequency Dispersion.



$$\epsilon'(\omega, T) = \epsilon_{\infty} + \Delta\epsilon \int_{-\infty}^{\infty} \frac{g(\tau, T) \ln \tau}{1 + (\omega\tau)^2}$$

Relaxors. Nanodomains.

PNR – polar nanodomains
COR – chemically ordered regions






Figure 3.

(a) ABO₃ perovskite structure. (b) Model for relaxor structure. PNR and COR represent the polar nano-region and chemically order region, respectively. (c) & (d) show two models of atom arrangement for COR. To maintain the electric neutrality, a Nb-rich layer is required for case (c).

Relaxors. Field Induced Ferroelectric Transition..




$T > T_f$




$T < T_f$

Rhombohedral distortion







E_{DC} is applied in (111) direction
 T_f – temperature of the induced
relaxor – ferroelectric transition

PMN. Field Induced. Ferroelectric Transition.



E-T phase
in (111) c



(s)


Solid solution relaxor-regular ferroelectric.

$(\text{PMN})_{0.97}(\text{PT})_{0.03}$

$(\text{PMN})_{(1-x)}(\text{PT})_x$
phase diagram



610K




PT: PbTiO_3 , ferroelectric with Curie temperature 763K


$(\text{PMN})_{0.6}(\text{PT})_{0.4}$




$(\text{PMN})_{0.9}(\text{PT})_{0.1}$



$(\text{PMN})_{0.7}(\text{PT})_{0.3}$




Applications of ferroelectrics



Applications. Nonvolatile Memory



Fast write speed (65-70ns)
High endurance (10^{14} cycles)
Low power consumption



APPLIED PHYSICS LETTERS **102**, 201118 (2013)



Terahertz plasmonics in ferroelectric-gated graphene


Dafei Jin,¹ Anshuman Kumar,¹ Kin Hung Fung,^{1,2} Jun Xu,¹ and Nicholas X. Fang¹

¹Department of Mechanical Engineering, Massachusetts Institute of Technology, Cambridge, Massachusetts 02139, USA

²Department of Applied Physics, The Hong Kong Polytechnic University, Hong Kong, China




Applications. Actuators



Piezo-injector for diesel engines, (b) Multilayer piezoelectric actuator scheme.

Courtesy Technische Universität Darmstadt

Atomic Force Microscope




Lead Zirconium Titanate piezo scanner

PI (www.pi.ws)



Applications. Sonars

Military Applications



Piezocomposite materials have been tested by the United States military since 1992.



APPLICATIONS:

MINE HUNTING
WEAPONS SONAR
COUNTERMEASURES
ACOUSTIC COMMUNICATIONS
PROJECTOR ARRAYS
HYDROPHONE ARRAYS
VIBRATION CONTROL

Applications. Sonars


Civil Applications




Fish Finder

Courtesy **FURUNO**

Applications. Adaptive Optics




Soldered control and mass wires



Reflecting surface

PZT – Lead Zirconium Titanate $Pb[Zr_xTi_{1-x}]O_3$




Courtesy of

Active Structures Laboratory

<http://scmero.ulb.ac.be>

Ferroelectricity: Relaxors - applications



Actuators
 Transducers
 Adaptive optics
 Capacitors
 Line motors for SFM



Transducer stack for ultrasonic sonar application (TRS Ceramics)

Material	Dielectric constant	Piezoelectric coefficient, (pC/n)	Electromechanical coupling factor
Quartz	4.5	2.3	0.1
Rochelle salt (30C)	9.2	27	0.3
Barium titanate ceramic	1700	190	0.52
Lead zirconate titanate PZT 45/55	450	140	0.60
PMN-PT (sc)	4200	2200	0.92-0.94
PZN-PT (sc)	2500	2400	0.91-0.93

Piezoelectric properties of different materials